

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): An assembly comprising:

a wood floor directly above and in contact with a material ~~comprising~~ consisting of a felt of mineral fibers, the material ~~comprising~~ consisting of a felt of mineral fibers configured to specifically attenuate a noise of an impact with the wood floor emitted in a same room as the wood floor,

wherein the felt includes binder that is in an amount from 3 to 30% by weight.

Claim 2 (Previously Presented): The assembly as claimed in claim 1, wherein the felt has a thickness ranging from 2 to 10 mm.

Claim 3 (Previously Presented): The assembly as claimed in claim 2, wherein the felt has a thickness ranging from 3 to 7 mm.

Claim 4 (Previously Presented): The assembly as claimed in claim 1, wherein the fibers of the felt have a fineness index ranging from 3 to 25 liters per minute.

Claim 5 (Previously Presented): The assembly as claimed in claim 1, wherein the fibers of the felt have a fineness index ranging from 10 to 15 l/min.

Claim 6 (Previously Presented): The assembly as claimed in claim 1, wherein the mineral fibers are glass fibers.

Claim 7 (Cancelled).

Claim 8 (Previously Presented): The assembly as claimed in claim 1, wherein the binder is in an amount from 5 to 25% by weight.

Claim 9 (Previously Presented): The assembly as claimed in claim 8, wherein the binder is in an amount from 6 to 16% by weight.

Claim 10 (Previously Presented): The assembly as claimed in claim 1, wherein the binder is of the thermosetting type.

Claim 11 (Previously Presented): The assembly as claimed in claim 1, wherein the binder is of the phenolic or acrylic or epoxy type.

Claim 12 (Previously Presented): The assembly as claimed in claim 1, wherein the fibers were produced by the internal centrifugation process.

Claim 13 (Previously Presented): The assembly as claimed in claim 1, wherein the material includes at least one veil.

Claim 14 (Previously Presented): The assembly as claimed in claim 13, wherein the at least one veil is on an external face of the assembly.

Claim 15 (Previously Presented): The assembly as claimed in claim 13, wherein the at least one veil has a mass per unit area ranging from 5 to 100 g/m².

Claim 16 (Previously Presented): The assembly as claimed in claim 13, wherein the at least one veil is made of polyester.

Claim 17 (Previously Presented): The assembly as claimed in claim 1, wherein the material and the wood floor are adhesively bonded to each other.

Claim 18 (Previously Presented): The assembly as claimed in claim 1, wherein the wood floor is a laminate.

Claim 19 (Previously Presented): A building that includes an assembly as claimed in claim 1.

Claim 20 (Currently Amended): A material consisting of a felt ~~comprising of~~ mineral fibers, with a thickness ranging from 2 to 10 mm and a mass per unit area of at least 130 g/m² configured to specifically attenuate a noise of an impact with a wood floor emitted in a same room as the felt and the wood floor, wherein the felt includes binder that is in an amount from 3 to 30% by weight.

Claim 21 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the mass per unit area ranges from 180 to 700 g/m².

Claim 22 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the felt has a thickness ranging from 3 to 7 mm.

Claim 23 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the mineral fibers have a fineness index ranging from 3 to 25 liters per minute.

Claim 24 (Currently Amended): The ~~felt~~ material as claimed in claim 23, wherein the mineral fibers have a fineness index ranging from 10 to 15 l/min.

Claim 25 (Cancelled).

Claim 26 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the binder is in an amount from 5 to 25% by weight.

Claim 27 (Currently Amended): The ~~felt~~ material as claimed in claim 26, wherein the binder is in an amount from 6 to 16% by weight.

Claim 28 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the binder is of the thermosetting type.

Claim 29 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the binder is of the phenolic or acrylic or epoxy type.

Claim 30 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the fibers are produced by the internal centrifugation process.

Claim 31 (Currently Amended): The ~~felt~~ material as claimed in claim 20, wherein the mineral fibers are glass fibers.

Claim 32 (Currently Amended): A method of using a material ~~including~~ consisting of a felt of mineral fibers, comprising:

placing said material on a floor base and directly under and in contact with a wood floor in a room, in order to specifically attenuate the impact noise created in the room caused by an impact with said wood floor.

Claim 33 (Previously Presented): The method as claimed in claim 32, further comprising:

placing the material, without adhesive bonding, into the floor base.

Claim 34 (Currently Amended): An assembly comprising:

a wood floor directly above and in contact with a material ~~comprising~~ consisting of a felt of mineral fibers, the material comprising a felt of mineral fibers configured to specifically attenuate a noise of an impact with the wood floor emitted in a same room as the wood floor.

Claim 35 (Previously Presented): The assembly as claimed in claim 34, wherein the felt has a thickness ranging from 2 to 10 mm.

Claim 36 (Previously Presented): The assembly as claimed in claim 35, wherein the felt has a thickness ranging from 3 to 7 mm.

Claim 37 (Previously Presented): The assembly as claimed in claim 34, wherein the fibers of the felt have a fineness index ranging from 3 to 25 liters per minute.

Claim 38 (Previously Presented): The assembly as claimed in claim 34, wherein the fibers of the felt have a fineness index ranging from 10 to 15 l/min.

Claim 39 (Previously Presented): The assembly as claimed in claim 34, wherein the mineral fibers are glass fibers.

Claim 40 (Previously Presented): The assembly as claimed in claim 34, wherein the binder is of the thermosetting type.

Claim 41 (Previously Presented): The assembly as claimed in claim 34, wherein the binder is of the phenolic or acrylic or epoxy type.

Claim 42 (Previously Presented): The assembly as claimed in claim 34, wherein the fibers were produced by the internal centrifugation process.

Claim 43 (Previously Presented): The assembly as claimed in claim 34, wherein the material includes at least one veil.